



Technical datasheet

A-Pox 5000

The epoxy is based on epoxy resin of Diglycidyl ether of Bisphenol-A + Diglycidyl ether of Bisphenol-F having reduced viscosity.

The epoxy has good mechanical strength and chemical resistance.

Good resistance against crystallization, and it can be stored at ambient temperature at least 12 months.

Typical applications:

A-Pox 5000 is recommended to be used with curing agent B-Cure 32, 43 or 50 for hand lay-up and industrial applications.

Typical Properties epoxy:

Epoxy Equivalent Weight (g/eq)	170-180
Viscosity (mPas / 25°C)	7400-8500
Density (g/cm ³ 25°C)	1.15-1.16
Color (Gardner)	<2

Handling precautions:

Product may cause skin and eye irritation. In cases of skin contact wash immediately with soap and water. For eyes, flush with plenty of water for 15 minutes and seek medical attention immediately.

AXL/29.05.2013